

S/N 10/763,625

Response to Office Action Dated 01 December 2005

In the Claims

1. 1—37 (Cancel)

38. (New.) A coated substrate configured for printing a toner image thereon, comprising:

a substrate;

an underlayer coating, applied directly on the substrate, wherein the underlayer coating comprises amine terminated polyamide; and

an overlayer coating, applied directly on the underlayer coating, comprising a polymer material to which the toner image can be fused and fixed.

39. (New.) The coated substrate according to claim 38, wherein the substrate is selected from among a group of substrates comprising polyethylene, vinyl, paper, polyethylene terephthalate (PET), BOPP (biaxially oriented polypropylene film) and polycarbonate.

40. (New.) The coated substrate according to claim 38 wherein the overlayer coating is free of particulate matter.

41. (New.) The coated substrate according to claim 38 wherein the polymer material comprises styrene butadiene copolymer.

S/N 10/763,625

Response to Office Action Dated 01 December 2005

1 42. (New.) The coated substrate according to claim 38 wherein the
2 polymer material comprises ethylene acrylic acid copolymer.
3

4 43. (New.) A print media for printing a toner image thereon,
5 comprising:
6

7 a substrate coated with an underlayer having a high affinity for the
8 substrate, and an overlayer having a high affinity for toner, wherein the underlayer
9 and the overlayer have high affinity for each other;

10 wherein the underlayer is applied directly to the substrate and comprises
11 amine terminated polyamide; and

12 wherein the overlayer is applied directly to the underlayer and comprises a
13 polymer material defining an outer surface to which the toner image can be fused
14 and fixed.
15

16
17 44. (New.) The print media according to claim 43, wherein the substrate
18 is selected from among a group of substrates comprising polyethylene, vinyl,
19 paper, polyethylene terephthalate (PET), BOPP (biaxially oriented polypropylene
20 film) and polycarbonate.
21

22 45. (New.) The print media according to claim 43 wherein the
23 underlayer is free of particulate matter.
24
25

S/N 10/763,625

Response to Office Action Dated 01 December 2005

1 46. (New.) The print media according to claim 43 wherein the overlayer
2 comprises styrene butadiene copolymer.

3
4 47. (New.) The print media according to claim 43 wherein the overlayer
5 comprises ethylene acrylic acid copolymer.

6
7 48. (New.) A method of producing a coated substrate to which a toner
8 image can be adhered, comprising:

9 coating a substrate with an underlayer comprising amine terminated
10 polyamide; and

11 coating the underlayer with a polymer material to form an overlayer on the
12 underlayer, wherein the overlayer has a high affinity for the underlayer and an
13 outer surface to which the toner image can be applied.
14

15
16 49. (New.) The method of claim 48, wherein coating the substrate
17 comprises:

18 coating a paper substrate.
19
20

21 50. (New.) The method of claim 48, wherein coating the substrate
22 comprises:

23 coating a plastic sheet substrate.
24
25

S/N 10/763,625

Response to Office Action Dated 01 December 2005

1 51. (New.) The method of claim 48, wherein coating the substrate
2 comprises applying 0.1 to 0.3 grams of solids to the substrate per square meter of
3 the substrate.

4
5 52. (New.) The method of claim 48, wherein coating the substrate
6 comprises:

7 mixing a 19-to-1 ratio of 1-Propanal to Macromelt 6239 (Henkel);
8 stirring the mixture; and
9 heating the mixture to between 40 degrees C. and 50 degrees C., until a
10 homogeneous and clear 5% solids solution is obtained.
11

12
13 53. (New.) The method of claim 48, wherein coating the substrate
14 comprises:

15 coating the substrate with a partial solids solution; and
16 letting the partial solids solution dry.
17

18
19 54. (New.) The method of claim 53, wherein the partial solids solution
20 is a 5% solids solution.
21
22
23
24
25

S/N 10/763,625

Response to Office Action Dated 01 December 2005

1 55. (New.) The method of claim 48, wherein coating the underlayer
2 comprises:

3 combining deionized water and isopropyl alcohol to form a mixture;
4 cooling the mixture; and
5 adding the mixture to a dispersion of MP 4990.
6

7 56. (New.) The method of claim 55, wherein the dispersion of MP 4990
8 is in a range of 32% to 35%.
9

10
11 57. (New.) The method of claim 48, wherein coating the underlayer
12 comprises:

13 applying 0.3 to 0.5 grams of the polymer material per square meter of
14 underlayer.
15

16
17 58. (New.) The method of claim 48, wherein coating the underlayer
18 comprises:

19 drying the underlayer before applying the outerlayer.
20
21
22
23
24
25